


# **SPO 40/B**

# **Omega profile**



## GENERAL DESCRIPTION

The SPO profile with 'OMEGA' section, thanks to its geometry together with the dots on the surface, facilitates positioning and screwing. It is mounted on rails according to UNI and DIN standards and is mainly used for the construction of false ceilings, self-standing false ceilings and false walls, with plasterboard cladding.

#### MATERIAL USED


The profile is made of carbon steel type **DX51D Z100**, continuously hot-dip galvanised, having a yield strength greater than 300 N/mm<sup>2</sup> and defined by European standard EN 10346 with a zinc coating of 100 g/m<sup>2</sup> (higher grammage on request).


Additional coatings consist of:


- Zinc-aluminium type **DX51D+AZ**: this combination gives the profile excellent corrosion resistance, superior to that of galvanised steel profiles, making them suitable for both indoor and outdoor use.
- Zinc-magnesium type **DX51D+ZM**: This type of coating gives the profile an extraordinary degree of corrosion protection on the surface and is self-healing on the cut edges, making it suitable for even the harshest environments.

#### REPRESENTATION

40







## ADVANTAGES AND APPLICATIONS OF THE SPO 40/B PROFILE -


The **SPO 40/B** profile has features that offer a quick and effective mounting system; it has a dot on the base of the profile that ensures precise fixing and can be adapted to individual needs

-Profile suitable for application with **G50** UNI and DIN

#### \*The information marked individually by ink on the side of each profile are:


GUERRASIO ID - PRODUCT IDENTIFICATION - DIMENSIONS - CE REGULATION - EUROPEAN NORM - DATE - TIME

#### **FASTENING TO THE FLOOR**



SPO 40/A with **G50** 

#### **FASTENING TO THE PERIMETER**



SPO 40/A with **G50** 

### **NORMATIVE REFERENCES –**

- Construction product in accordance with Regulation (EU) 305/2011
- EC marking in accordance with EN 14195
- Sheet metal quality and coating grade in accordance with EN 10143 and EN 10346

#### EC MARKING —

The products listed in this catalogue are intended for use inside buildings. Each product is provided with a Declaration of Performance (DoP). Reaction to fire: class A1/Durability: class B (building components exposed to variable relative humidity up to 90% and variable temperatures up to 30°C but without corrosive contaminants, except class C5-M products).

## PRODUCT STORAGE —

Store the packs in a covered areas with a relatively dry atmosphere and at a temperature as constant as possible, in order to avoid condensation which may reduce the state of passivation protecting the galvanised surface. If stored outdoors (not recommended), use a cover that provides perfect protection of the material against the weather (rain, fog, snow), taking care to place the packages at a slight angle. This cover must in any case be such as to allow adequate ventilation (not bringing the two surfaces into direct contact) so that moisture does not accumulate and create condensation.

## PACKAGING MATERIAL —

The package is made with plastic strips. The pallet is made using plastic strips, wooden supports and laths. The packaging is suitably sized to facilitate handling in warehouses and on construction sites.


## **TECHNICAL DATA** -

CHARACTERISTIC	REFERENCE NORM	VALUE	UNIT OF MEASUREMENT
Туре	EN 14195	Metal structure	-
Reaction to fire	EN 14195-1A	1	-
Standard thickness	EN 10143	0,6 - 0,8	mm
Thickness tolerance	EN 10143	± 0,07	mm
Length	EN 14195	3000-4000	mm
Length tolerance	EN 14195	± 4	mm
Protective coating	EN 10346	5 ÷ 12	μm
Yield stress	EN 10143	340	N/mm2

## **PACKING AND PALLET SHEET -**



Profile weight	Kg/lm	0,557		
	Kg/pc	3 lm ——— 4 lm —— 1,671 2,228		
Profile pieces	N°	10		
Total per package	lm	30 3 lm		
	Kg	16,71		
	lm	40 4 lm		
	Kg	22,28		
Dimensions	mm	65 70 3000 <sup>3 lm</sup>		
		65 70 4000 4 lm		



Packages	Pcs	30	
Total profiles	Pcs	300	
Total per pallets	lm	900	3 lm
	Kg	501	
	lm	1200	4 lm
	Kg	684	
Dimensions	mm	400 400 3000 d e f	3 lm
	mm	400 400 4000 d e f	4 lm

Total calculated on 6/10 thickness

**N.B.** -The weight of the package/pallet is subject to variation depending on the material tolerances described in the table.

-All technical data and characteristics given in the data sheet are subject to change without notice.